



## Sequoia sempervirens (D. Don) Endl.

### Family: Taxodiaceae

### Redwood

The genus *Sequoia* is represented by one species (*S. sempervirens*). A related tree, the giant sequoia (*Sequoiadenrdon giganteum*) is also called redwood, big tree or giant redwood. The word sequoia was selected to honor Sequoyah (also spelled Sequoia), or George Guess (1770?-1843), Native American inventor of the Cherokee alphabet. The name was unexplained by its author, an Austrian linguist and botanist. The name *sempervirens* means evergreen.

**Other Common Names:** Amerikansk sekvoja, California cedar, California redwood, Californische redwood, coast redwood, corla, giant-of-the-forest, Humboldt redwood, ledwood, Mexican cherry, palo colorado, pin rouge d'ambrique, pin rouge d'Amerique, pino rosso d'america, redwood, sequoia, sequoia de California, sequoia roja, sequoia rossa, sequoia toujours vert, sequoie, vavona, vavona burr.

**Distribution:** Redwood is native to the Pacific Coast region from extreme southwestern Oregon (Curry County) south to central California (Monterey County).

**The Tree:** Redwood trees reach heights of 200 to 300 feet, with diameters of 6 to 12 feet. The record is 376 feet tall, with a 20 foot diameter and an age of 2,200 years, and represents the world's tallest tree.

**General Wood Characteristics:** The sapwood of is white, while the heartwood is a dark reddish brown. The heartwood has no characteristic odor or taste. It has exceptionally straight grain, high dimensional stability and is resistant to warping. It is moderately strong in bending, strong in endwise compression, stiff, moderately low in shock resistance and holds paint well.

#### Weight

Moisture content	Specific gravity		
<b>Old Growth</b>			
Green	0.38 <sup>a</sup>		
12%	0.40 <sup>a</sup>		
Ovendry	0.42 <sup>b</sup>		
<b>Second Growth</b>			
Green	0.34 <sup>a</sup>		
12%	0.35 <sup>a</sup>		
Ovendry	0.36 <sup>c</sup>		

<sup>a</sup>Reference (15).

<sup>b</sup>Reference (14).

<sup>c</sup>Reference (9).

#### Mechanical Properties<sup>a</sup>

Property	Green	Dry
<b>Old Growth</b>		
MOE	8.14 GPa	9.24 GPa
MOR	51.7 MPa	69.0 MPa
C <sub>  </sub>	29.0 MPa	42.4 MPa
C <sup>^</sup>	2.90 MPa	4.83 MPa
WML	51.0 kj/m <sup>3</sup>	47.6 kj/m <sup>3</sup>

Hardness	1820 N	2130 N
Shear <sub>r </sub>	5.52 MPa	6.48 MPa
<b>Second Growth</b>		
MOE	6.62 GPa	7.58 GPa
MOR	40.7 MPa	54.5 MPa
C <sub> </sub>	21.4 MPa	36.0 MPa
C <sup>^</sup>	1.86 MPa	3.58 MPa
WML	39.3 kj/m <sup>3</sup>	35.8 kj/m <sup>3</sup>
Hardness	1560 N	1870 N
Shear <sub>r </sub>	6.14 MPa	7.65 MPa

### Drying and shrinkage

Type of shrinkage	Percentage of shrinkage (green to final moisture content)		
	0%MC <sup>a</sup>	6%MC <sup>b</sup>	20%MC <sup>b</sup>
<b>Old Growth</b>			
Tangential	4.4	3.5	1.5
Radial	2.6	2.1	0.9
Volumetric	6.8	5.4	2.3
<b>Second Growth</b>			
Tangential	4.9	NA	NA
Radial	2.2	NA	NA
Volumetric	7.0	NA	NA

<sup>a</sup>Reference (15).

<sup>b</sup>Reference (14).

### Kiln Drying Schedules<sup>a</sup>

#### Conventional Temperatures/Moisture Content-Controlled Schedules<sup>a</sup>

Condition	4/4, 5/4 stock	6/4 stock	8/4 stock	10/4 stock	12/4 stock	British Schedule 4/4 stock
Light	T5-D6	NA	T5-D4	T5-C4	T5-C3	K
Heavy	T4-F5	T3-F5	T3-F4	NA	NA	NA

<sup>a</sup>Reference (2&13).

#### Conventional Temperatures/Time-Controlled Schedules<sup>a</sup>

Condition	Lower Grades			Upper grades			
	4/4, 5/4 stock	6/4 stock	8/4 stock	4/4, 5/4 stock	6/4 stock	8/4 stock	12/4, 16/4 stock
Light	289	288	b	289	288	b	NA
Medium & Heavy	c	c	c	c	c	c	NA

<sup>a</sup>References (2&13).

<sup>b</sup>Air dry to 20% MC, then dry using table 286 (13).

<sup>c</sup>Air dry to 20% MC, then dry using table 289. Prone to collapse(13).

**Working Properties:** Redwood works easily with both hand and machine tools, with little dulling effect on tools. It planes well, provided the cutters are sharp and it splinters easily when working on the end grain. It holds nails well, and paints and finishes satisfactorily. It also stains well, but glues best with alkaline adhesives.

**Durability:** Redwood is rated as resistant to very resistant to heartwood decay.

**Preservation:** Redwood is moderately resistant to preservative treatments.

**Uses:** High value building construction, heavy beams, bridge timbers, planks, siding, sash, doors, veneer, furniture, cooling equipment, plywood, pulping, particle board, shakes, shingles, grape stakes, posts and novelties (from burl wood).

**Toxicity:** Working with redwood may cause allergic reactions (4,10&16).

#### Additional Reading and References Cited (in parentheses)

1. Betts, H. S. Redwood (*Sequoia sempervirens*). Washington, DC, USA.: USDA Forest Service, USGPO, O-940471; 1945.
2. Boone, R. S.; Kozlik, C. J.; Bois, P. J., and Wengert, E. M. Dry kiln schedules for commercial woods - temperate and tropical. Madison, WI: USDA Forest Service, FPL-GTR-57; 1988.
3. Dallimore, W.; Jackson, A. B., and Harrison, S. G. A handbook of Coniferae and Ginkgoaceae. London, UK: Edward Arnold Ltd.; 1966.
4. Hausen, B. M. Woods injurious to human health. A manual. New York, NY: Walter de Gruyter; 1981.
5. Henderson, F. Y. A handbook of softwoods. London: HMSO; 1977.
6. Lindquist, J. L. Redwood, an American wood. Washington, DC, USA.: USDA Forest Service, FS-262.; 1974.
7. Little, jr. E. L. Checklist of United States trees (native and naturalized). Washington, DC: USGPO, USDA Forest Service, Ag. Handbook No. 541; 1979.
8. Luxford, R. F. and Markwardt, L. J. The strength and related properties of redwood. Washington, DC, USA.: USDA Forest Service, Technical Bulletin No. 305; 1932.
9. Markwardt, L. J. and Wilson, T. R. C. Strength and related properties of woods grown in the United States. Washington, DC: USGPO, USDA Forest Service, Tech. Bull. No. 479; 1935.
10. Mitchell, J. and Rook, A. Botanical dermatology: plants and plant products injurious to the skin. Vancouver, BC: Greenglass Ltd.; 1979.
11. Olson, Jr. D. F.; Roy, D. F., and Walters, G. A. *Sequoia sempervirens* (D. Don) Endl. in: Burns, R. M. and Honkala, B. H., tech. coords. Silvics of North America. Volume 1, Conifers. Washington, DC: USDA Forest Service; 1990; pp. 541-551.
12. Show, S. B. and Stuart, R. Y. Timber growing and logging practice in the coast redwood region of California. Washington, DC, USA: USDA Forest Service, Technical Bulletin No. 283; 1932.
13. Simpson, W. T. Dry kiln operator's manual. Madison, WI: USDA Forest Service, FPL Ag. Handbook No. 188; 1991.
14. Summitt, R. and Sliker, A. CRC handbook of materials science. Vol. 4. Boca Raton, FL: CRC Press, Inc.; 1980.
15. USDA. Wood handbook: wood as an engineering material. Madison, WI: USDA Forest Service, FPL Ag. Handbook No. 72; 1974.
16. Woods, B. and Calnan, C. D. Toxic woods. British Journal of Dermatology. 1976; 95(13):1-97.